CONTEGA® SOLIDO EXO-D

Full-surface adhesive plaster/window-sealing tape with an additional adhesive zone, for exterior use



Technical data

	Material
Backing	PP backing fleece, PP copolymer special film
Adhesive	Modified water-resistant SOLID adhesive
Release film	Single/double-split silicone-coated PE sheet

Property	Regulation	Value
Colour		Black
Vapour resistance (MVTR)	EN 1931	3.5 MN·s/g
UV stability and outdoor exposure		3 months
Resistance to driving rain	ift, MO-01/1:2007-01, Abs. 5	Up to 600 Pa, around window
Water column	EN ISO 811	> 2 500 mm
Can be plastered over		Yes
Application temperature		Above -10 °C
Temperature resistance		Permanent -40 °C to +90 °C
Storage		Cool and dry

Areas of application

For exterior windtight joints that are resistant to driving rain between membranes or wood-based panels and windows, doors and mineral surfaces. The adhesive zone on the fleece side allows for easier adhesion to windows and doors if applied before they are installed. The taped joint is immediately windproof and can be subjected to loading. The fleece can simply be plastered over in accordance with the installation instructions.

Supply forms

Art. no.	Length	Width	Release film splits	Weight	Sales unit	Container	GTIN
16135	30 m	80 mm	20 | 60 mm	1.1 kg	8	288	4026639161352

Advantages

- ✔ Saves time: the joint is immediately resistant to driving rain and can be subjected to loading
- ✔ Easy to work with thanks to the additional adhesive zone on the fleece side
- ✔ Can be plastered over directly: defined transition between window and/or wind sealing and plasterwork
- ✔ Reliable joints: water-resistant SOLID adhesive has extremely strong adhesion on mineral subsurfaces too
- ✔ Independently confirmed suitability: tests in accordance with MO-01/1 passed at IFT in Rosenheim, Germany

Substrates

Clean subsurfaces before sticking. Uneven mineral subsurfaces may need to be levelled with a smooth plaster finish. Adhesion to frozen surfaces is not possible. There must be no water-repellent substances (e.g. grease or silicone) on surfaces where adhesives are to be applied.

Observe the recommendations for plastering over adhesive tapes that are specified by the producer of the plaster. In most cases, it is recommended that the width of adhesive tape that is to be plastered over should not exceed 60 mm or 50% of the reveal area. Subsurfaces must be sufficiently dry and stable; if necessary, subsurfaces should be stabilised or renewed.

Permanent adhesion is achieved on all pro clima exterior membranes and on other underlay and breather (WRB) membranes (e.g. those made of PP and PET). Tapes can be applied to planed or painted wood, hard plastics, hard wood-based panels (chipboard, OSB and plywood panels). For sealing joints on masonry or concrete or on rough substrates, use ORCON F.

The best results in terms of reliability are achieved on high-quality subsurfaces. Particular care is necessary when working with older or multi-layer subsurfaces. It is your responsibility to check the suitability of the subsurface; adhesion tests may be necessary in certain cases. Pre-treatment of the subsurface with TESCON PRIMER will improve the adhesive bond.

General conditions

Taped joints must not be subjected to tensile forces.
Rub the adhesive tapes firmly to secure the adhesive bonds. Ensure that there is sufficient resistance pressure.
Seals that are windproof and resistant to driving rain can only be achieved if the sealing tape is installed free of folds and breaks.
When plastering, please observe the recommendations of the plaster manufacturer for non-absorbent subsurfaces. A bonding course may be necessary.



Prüfbericht Nr. 15-003305-PR01
(PB-E03-020310-de-02)
• CONTEGA SOLIDO SL-D
• CONTEGA SOLIDO EXO-D
nach MO-01/1:2007-01, Abs. 5
15.03.2016

Made in Germany developed and produced by pro clima

© 2026 Pro Clima New Zealand. All rights reserved. The trademarks in this document are registered to Pro Clima or one or more of its affiliates.

The information provided in this document is based on practical experience and current knowledge and was correct at the time of publication. Pro Clima reserves the right to change technical details as developments occur and improvements are made to our products.

Pro Clima recommends reviewing the latest technical data on the www.proclima.co.nz website to ensure the most current document version.

PRO CLIMA NEW ZEALAND
Upper North Island: 09 892 9900
Lower North Island: 04 589 8460
South Island: 03 327 4925
Technical: support@proclima.co.nz
General: welcome@proclima.co.nz
0800 PRO CLIMA (776 254)